

# 1100 Fast Set

## Urethane Adhesive/Sealant

### Product Description

Bostik® 1100 Fast Set is a one part urethane sealant that cures by reaction with atmospheric moisture to form a tough, flexible seal. It has tenacious adhesion to woods, metals, FRP and most plastics. Bostik 1100 Fast Set can be used in bonding, beading and sealing applications.

### Typical Applications

Sealing and bonding applications in general industry, HVAC, truck trailer, horse trailer, RV, emergency vehicle, bus, railcar, and container construction. Bostik1100FS should not be used for glazing, for plastic materials with high plasticizer content or corrosion/crack sensitive plastics.

### Applicable Standards

Bostik 1100FS meets requirements of:

- Federal Specification TT-S-00230C (COM-NBS) for one-component sealants as Class A, Non-Sag
- ASTM C920-79 Standard Specifications for Elastomeric Joint Sealants as type S, Grade NS, Class 25, Use NT, A and M
- Canadian Standard CAN/CGSB-19.13

### Clean Up

Uncured Bostik 1100 Fast Set may be easily removed from hands and tools with Bostik® Hand & Tool Towels. Excess sealant should be dry-wiped from all surfaces and tools while still uncured. Cured sealant can be removed with a sharp blade. NOTE: Cured sealant is usually very difficult to remove without altering or damaging the surface to which the sealant was applied.

### Shelf Life

When stored at or below 80°F (27°C), Bostik 1100FS polyurethane sealant has a shelf life of nine months from date of manufacture.



### Typical Uncured Properties\*

Property	Value
Tool/Work Life	70 minutes
Tack Free Time	90 minutes
Curing Time @77°F	1.5 - 3 days
Flow, Sag or Slump	Nil
Staining	None

### Typical Cured Properties\* (after 14 days cure at 77°F and 50% RH)

Property	Value
Hardness (Shore A)	40 - 45
Modulus @ 100% Elongation	65 psi
Tensile Strength	240 psi
Elongation	850%
Adhesion in Peel	>25 piw
Stain and Color Change	None
Ozone Resistance	Excellent
Joint Movement Capability	±25%
UV Resistance	Good
Heat and Aging	Good
Temperature Resistance	-40° to 180°F

\* Values given above are not intended to be used in specification preparation.

### IMPORTANT NOTICE

All statements, technical information and recommendations set forth herein are based on tests which Bostik, Inc. believes to be reliable. However, Bostik does not guarantee their accuracy or completeness. The buyer should conduct its own tests of this product before use to determine proper preparation technique and suitability for proposed application. Any sales of this product shall be on terms and conditions set forth on Bostik's order acknowledgment. Bostik, Inc. warrants that the product conforms with Bostik written specifications, and is free from defects. BOSTIK, INC. DISCLAIMS ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING THE WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. THE BUYER'S SOLE REMEDY FOR NONCOMPLIANCE WITH THIS WARRANTY SHALL BE FOR THE REPLACEMENT OF THE PRODUCT OR REFUND OF THE BUYER'S PURCHASE PRICE. IN NO CASE WILL BOSTIK, INC. BE LIABLE FOR DIRECT, CONSEQUENTIAL ECONOMIC OR OTHER DAMAGES.